

Technical Data Sheet

Trihexyltetradecylphosphonium bis(trifluoromethylsulfonyl)imide

 Revision Date:
 12/22/2011

 Date Issued:
 2/8/2022

1 IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND THE COMPANY/UNDERTAKING

Product name	Trihexyltetradecylphosphonium bis(trifluoromethylsulfonyl)imide	
Product code	IN-0021	
CAS	460092-03-9	
Supplier	IoLiTec Ionic Liquids Technologies GmbH ROCO Im Zukunftspark 9 D – 74076 Heilbronn Germany I816 Parkway View Drive ,	
Telephone	+49 (0)7131-89839-0	Pittsburgh, PA 15205
Fax	+49 (0)7131-89839-109	Info@roco.global
Emergency telephone	+49 (0)179-5322578	724-315-9170
Email	info@iolitec.de	www.roco.global

2 COMPOSITION/INFORMATION ON INGREDIENTS

Ingredient name

CAS No.

Empirical Formula

Trihexyltetradecylphosphonium bis(trifluoromethylsulfonyl)imide 460092-03-9 C₃₄H₆₈F₆NO₄PS₂

 $(CF_3SO_2)_2N^{\ominus}$

Structure Molecular weight Purity

763.24 g/mol >98%



Technical Data Sheet

Trihexyltetradecylphosphonium bis(trifluoromethylsulfonyl)imide

 Revision Date:
 12/22/2011

 Date Issued:
 2/8/2022

3 PROPERTIES

Color	Yellow to orange
Physical state (25 °C)	Liquid
Melting point	-72 °C
Glass transition temperature	not available
Decomposition temperature	not available
Density (23 °C)	1.065 g/cm ³
Viscosity (25 °C)	286 mPa * s
Heat capacity (20 °C)	not available
Conductivity (30 °C)	0.155 mS/cm
Electrochemical stability window	4.4 V
Anodic limit	2.5 V
Cathodic limit	-1.9 V

4 CO-SOLVENT MISCIBILITY

scible
le



Technical Data Sheet

Trihexyltetradecylphosphonium bis(trifluoromethylsulfonyl)imide

 Revision Date:
 12/22/2011

 Date Issued:
 2/8/2022

5 ORDER INFORMATION

IN-0021-HP can be obtained in the following standard quantities:

Quantity	Price
25 g	Please enquire
50 g	Please enquire
100 g	Please enquire
250 g	Please enquire
500 g	Please enquire
1 kg	Please enquire
Bulk	Please enquire

Please send your order via email to order@iolitec.de or fax +49 (0)7131 - 89839109.

6 OTHER INFORMATION

DISCLAIMER

THE ABOVE INFORMATION IS BELIEVED TO BE CORRECT BUT DOES NOT PURPOSED TO BE ALL INCLUSIVE AND SHALL BE USED ONLY AS A GUIDE. IOLITEC SHALL NOT BE HELD LIABLE FOR ANY DAMAGE RESULTING FROM HANDLING OR FROM CONTACT WITH THE ABOVE PRODUCT. THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR ANY PROCESS. IT IS THE USERE'S RESPONISIBILTY TO SATISFY HIMSELF AS TO THE SUITABILITY OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE.

IN NO WAY SHALL IOLITEC BE LIABLE FOR ANY CLAIMS, LOSSES OR DAMAGES OF ANY THIRD PARTY OR FOR THE LOST PROFITS OR ANY SPECIAL, INDIRECT, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES, HOWSOEVER ARISING, EVEN IF THE COMPANY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.