

# Technical Data Sheet

## Triethylsulfonium bis(trifluoromethylsulfonyl)imide


Revision Date: 1/19/2012

Date Issued: 10/31/2012

### 1 IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND THE COMPANY/UNDERTAKING

<b>Product name</b>	Triethylsulfonium bis(trifluoromethylsulfonyl)imide
<b>Product code</b>	IL-0030
<b>CAS</b>	321746-49-0
<b>Supplier</b>	IoLiTec Ionic Liquids Technologies GmbH Salzstrasse 184 D – 74076 Heilbronn Germany
<b>Telephone</b>	+49 (0)7131-89839-0
<b>Fax</b>	+49 (0)7131-89839-109
<b>Emergency telephone</b>	+49 (0)179-5322578
<b>Email</b>	info@iolitec.de

### 2 COMPOSITION/INFORMATION ON INGREDIENTS

<b>Ingredient name</b>	Triethylsulfonium bis(trifluoromethylsulfonyl)imide
<b>CAS No.</b>	321746-49-0
<b>Empirical Formula</b>	$C_8H_{15}F_6NO_4S_3$
<b>Structure</b>	
<b>Molecular weight</b>	399.39 g/mol
<b>Purity</b>	>99%

# Technical Data Sheet

## Triethylsulfonium bis(trifluoromethylsulfonyl)imide

Revision Date: 1/19/2012

Date Issued: 10/31/2012

---

### 3 PROPERTIES

<b>Color</b>	Colorless to yellow
<b>Physical state (25 °C)</b>	liquid
<b>Melting point</b>	-35 °C
<b>Glass transition temperature</b>	not available
<b>Decomposition temperature</b>	not available
<b>Density (24 °C)</b>	1.462 g/cm <sup>3</sup>
<b>Viscosity (20 °C)</b>	39 mPa * s
<b>Heat capacity (25 °C)</b>	not available
<b>Conductivity (25 °C)</b>	5.116 mS/cm
<b>Electrochemical stability window</b>	4.5 V
<b>Anodic limit</b>	2.7 V
<b>Cathodic limit</b>	-1.8 V

### 4 CO-SOLVENT MISCIBILITY

<b>Water</b>	not miscible
<b>Acetone</b>	miscible
<b>Acetonitrile</b>	miscible
<b>Isopropanol</b>	not miscible
<b>Toluene</b>	not miscible
<b>Hexane</b>	not miscible

# Technical Data Sheet

## Triethylsulfonium bis(trifluoromethylsulfonyl)imide

Revision Date: 1/19/2012

Date Issued: 10/31/2012

---

### 5 ORDER INFORMATION

IL-0030-HP can be obtained in the following standard quantities:

Quantity	Price
25 g	Please enquire
50 g	Please enquire
100 g	Please enquire
250 g	Please enquire
500 g	Please enquire
1 kg	Please enquire
Bulk	Please enquire

Please send your order via email to [order@iolitec.de](mailto:order@iolitec.de) or fax +49 (0)7131 – 89839109.

### 6 OTHER INFORMATION

#### DISCLAIMER

THE ABOVE INFORMATION IS BELIEVED TO BE CORRECT BUT DOES NOT PURPOSED TO BE ALL INCLUSIVE AND SHALL BE USED ONLY AS A GUIDE. IOLITEC SHALL NOT BE HELD LIABLE FOR ANY DAMAGE RESULTING FROM HANDLING OR FROM CONTACT WITH THE ABOVE PRODUCT. THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR ANY PROCESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE.

IN NO WAY SHALL IOLITEC BE LIABLE FOR ANY CLAIMS, LOSSES OR DAMAGES OF ANY THIRD PARTY OR FOR THE LOST PROFITS OR ANY SPECIAL, INDIRECT, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY

# Technical Data Sheet

## Triethylsulfonium bis(trifluoromethylsulfonyl)imide

Revision Date: 1/19/2012

Date Issued: 10/31/2012

---

DAMAGES, HOWSOEVER ARISING, EVEN IF THE COMPANY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.