io·li·tec

# **Technical Data Sheet**

1-Butyl-1-methylpiperidinium chloride

Revision Date:	6/26/2018
Date Issued:	2/11/2022

# 1 IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND THE COMPANY/UNDERTAKING

Product name	1-Butyl-1-methylpiperidinium chloride	
Product code CAS	IL-0155 845790-13-8	
Supplier	IoLiTec Ionic Liquids Technologies Gmb Im Zukunftspark 9 D – 74076 Heilbronn Germany	<b>Distributor</b> 1816 Parkway View Drive,
Telephone Fax Emergency telephone Email	+49 (0)7131-89839-0 +49 (0)7131-89839-109 +49 (0)179-5322578 info@iolitec.de	Pittsburgh, PA 15205 Info@roco.global 724-315-9170 www.roco.global

## 2 COMPOSITION/INFORMATION ON INGREDIENTS

Ingredient name

CAS No. Empirical Formula chloride 845790-13-8

1-Butyl-1-methylpiperidinium

 $C_{10}H_{22}CIN$ 

 $\Theta_{\rm IO}$ 

191.74 g/mol 99%

Structure Molecular weight Purity

io·li·tec

# **Technical Data Sheet**

1-Butyl-1-methylpiperidinium chloride

Revision Date:	6/26/20
Date Issued:	2/11/20

18 )22

## **3 PROPERTIES**

Color	Yellow to brown
Physical state (25 °C)	solid
Melting point	>230 °C
Glass transition temperature	not available
Decomposition temperature	not available
Density	1,1073 g/cm <sup>3</sup>
Viscosity	not available
Heat capacity	not available
Conductivity	not available
Electrochemical stability window	not available
Anodic limit	not available
Cathodic limit	not available

## **4 CO-SOLVENT MISCIBILITY**

Water
Acetone
Acetonitrile
Isopropanol
Toluene
Hexane

miscible not miscible miscible miscible not miscible not miscible



# **Technical Data Sheet**

1-Butyl-1-methylpiperidinium chloride

Revision Date:6/26/2018Date Issued:2/11/2022

#### **5 ORDER INFORMATION**

IL-0155-HP can be obtained in the following standard quantities:

Quantity	Price
25 g	Please enquire
50 g	Please enquire
100 g	Please enquire
250 g	Please enquire
500 g	Please enquire
1 kg	Please enquire
Bulk	Please enquire

Please send your order via email to order@iolitec.de or fax +49 (0)7131 - 89839109.

## **6 OTHER INFORMATION**

## DISCLAIMER

THE ABOVE INFORMATION IS BELIEVED TO BE CORRECT BUT IS NOT PURPOSED TO BE ALL INCLUSIVE AND SHALL BE USED ONLY AS A GUIDE. IOLITEC SHALL NOT BE HELD LIABLE FOR ANY DAMAGE RESULTING FROM HANDLING OR FROM CONTACT WITH THE ABOVE PRODUCT. THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR ANY PROCESS. IT IS THE USER'S RESPONISIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE.

IN NO WAY SHALL IOLITEC BE LIABLE FOR ANY CLAIMS, LOSSES OR DAMAGES OF ANY THIRD PARTY OR FOR THE LOST PROFITS OR ANY SPECIAL, INDIRECT, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES, HOWSOEVER ARISING, EVEN IF THE COMPANY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.