

Technical Data Sheet

1-Ethyl-3-methylpyridinium bromide

Revision Date: 6/26/2018
Date Issued: 10/18/2022

1 IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND THE COMPANY/UNDERTAKING

Product name 1-Ethyl-3-methylpyridinium
bromide

Product code IL-0226

CAS 54778-76-6

Supplier IoLiTec
Ionic Liquids Technologies GmbH
Im Zukunftspark 9
D – 74076 Heilbronn
Germany

Telephone +49 (0)7131-89839-0

Fax +49 (0)7131-89839-109

Emergency telephone +49 (0)179-5322578

Email info@iolitec.de

ROCO

Distributor

1816 Parkway View Drive,
Pittsburgh, PA 15205

✉ info@roco.global

724-315-9170


www.roco.global

2 COMPOSITION/INFORMATION ON INGREDIENTS

Ingredient name 1-Ethyl-3-methylpyridinium
bromide

CAS No. 54778-76-6

Empirical Formula C₈H₁₂BrN

Structure 

Molecular weight 202.09 g/mol

Purity >99%

Technical Data Sheet

1-Ethyl-3-methylpyridinium bromide

Revision Date: 6/26/2018

Date Issued: 10/18/2022

3 PROPERTIES

Color	Yellow to brown
Physical state (25 °C)	solid
Melting point	142°C
Glass transition temperature	not available
Decomposition temperature	not available
Density	1,4935 g/cm ³
Viscosity	not available
Heat capacity	not available
Conductivity	not available
Electrochemical stability window	not available
Anodic limit	not available
Cathodic limit	not available

4 CO-SOLVENT MISCIBILITY

Water	miscible
Acetone	not miscible
Acetonitrile	miscible
Isopropanol	miscible
Toluene	not miscible
Hexane	not miscible

Technical Data Sheet

1-Ethyl-3-methylpyridinium bromide

Revision Date: 6/26/2018

Date Issued: 10/18/2022

5 ORDER INFORMATION

IL-0226-HP can be obtained in the following standard quantities:

Quantity	Price
25 g	Please enquire
50 g	Please enquire
100 g	Please enquire
250 g	Please enquire
500 g	Please enquire
1 kg	Please enquire
Bulk	Please enquire

Please send your order via email to order@iolitec.de or fax +49 (0)7131 – 89839109.

6 OTHER INFORMATION

DISCLAIMER

THE ABOVE INFORMATION IS BELIEVED TO BE CORRECT BUT IS NOT PURPOSED TO BE ALL INCLUSIVE AND SHALL BE USED ONLY AS A GUIDE. IOLITEC SHALL NOT BE HELD LIABLE FOR ANY DAMAGE RESULTING FROM HANDLING OR FROM CONTACT WITH THE ABOVE PRODUCT. THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR ANY PROCESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE.

IN NO WAY SHALL IOLITEC BE LIABLE FOR ANY CLAIMS, LOSSES OR DAMAGES OF ANY THIRD PARTY OR FOR THE LOST PROFITS OR ANY SPECIAL, INDIRECT, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES, HOWSOEVER ARISING, EVEN IF THE COMPANY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.