

Technical Data Sheet

1-Butyl-2-methylpyridinium bis(trifluoromethylsulfonyl)imide

Revision Date: 6/26/2018

Date Issued: 2/8/2022

1 IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND THE COMPANY/UNDERTAKING

Product name 1-Butyl-2-methylpyridinium
bis(trifluoromethylsulfonyl)imide

Product code IL-0228

CAS 384347-09-5

Supplier IoLiTec
Ionic Liquids Technologies GmbH
Im Zukunftspark 9
D – 74076 Heilbronn
Germany

Telephone +49 (0)7131-89839-0

Fax +49 (0)7131-89839-109

Emergency telephone +49 (0)179-5322578

Email info@iolitec.de

ROCO

Distributor

1816 Parkway View Drive,
Pittsburgh, PA 15205

✉ info@roco.global

724-315-9170


www.roco.global

2 COMPOSITION/INFORMATION ON INGREDIENTS

Ingredient name 1-Butyl-2-methylpyridinium
bis(trifluoromethylsulfonyl)imide

CAS No. 384347-09-5

Empirical Formula C₁₂H₁₆F₆N₂O₄S₂

Structure  (CF₃SO₂)₂N⁻

Molecular weight 430.39 g/mol

Purity 99%

Technical Data Sheet

1-Butyl-2-methylpyridinium bis(trifluoromethylsulfonyl)imide

Revision Date: 6/26/2018

Date Issued: 2/8/2022

3 PROPERTIES

Color	Orange to brown
Physical state (25 °C)	liquid
Melting point	<RT
Glass transition temperature	not available
Decomposition temperature	not available
Density (21 °C)	1.43 g/cm ³
Viscosity (25 °C)	91.5 mPa * s
Heat capacity	not available
Conductivity (25 °C)	1.03 mS/cm
Electrochemical stability window	4.2 V
Anodic limit	2.9 V
Cathodic limit	-1.3 V

4 CO-SOLVENT MISCIBILITY

Water	not miscible
Acetone	miscible
Acetonitrile	miscible
Isopropanol	miscible
Toluene	miscible
Hexane	not miscible

Technical Data Sheet

1-Butyl-2-methylpyridinium bis(trifluoromethylsulfonyl)imide

Revision Date: 6/26/2018

Date Issued: 2/8/2022

5 ORDER INFORMATION

IL-0228-HP can be obtained in the following standard quantities:

Quantity	Price
25 g	Please enquire
50 g	Please enquire
100 g	Please enquire
250 g	Please enquire
500 g	Please enquire
1 kg	Please enquire
Bulk	Please enquire

Please send your order via email to order@iolitec.de or fax +49 (0)7131 – 89839109.

6 OTHER INFORMATION

DISCLAIMER

THE ABOVE INFORMATION IS BELIEVED TO BE CORRECT BUT IS NOT PURPOSED TO BE ALL INCLUSIVE AND SHALL BE USED ONLY AS A GUIDE. IOLITEC SHALL NOT BE HELD LIABLE FOR ANY DAMAGE RESULTING FROM HANDLING OR FROM CONTACT WITH THE ABOVE PRODUCT. THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR ANY PROCESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE.

IN NO WAY SHALL IOLITEC BE LIABLE FOR ANY CLAIMS, LOSSES OR DAMAGES OF ANY THIRD PARTY OR FOR THE LOST PROFITS OR ANY SPECIAL, INDIRECT, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES, HOWSOEVER ARISING, EVEN IF THE COMPANY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.